



AMERICAN FLAMECOAT INC.

520 Eagleton Downs Drive - D
Pineville, NC 28134
O: 704.405.2550
F: 704.543.9772
www.americanflamecoat.com

Client: ELITIS INC.
21-07 41st AVENUE
LON ISLAND CITY, NY 11101

Test Report No: 116730
PO# ELITIS – ESSENCE DE BOIS_DRYADES – RM 428
Date: May 30, 2024

The sample submitted by the client as: ELITIS INC. - ESSENCE DE BOIS_DRYADES –
RM 428
(ADHERED)

DATE OF RECEIPT: 05.02.2024

TESTING PERIOD: 28 DAYS

TEST REQUESTED: The submitted sample was tested for flammability in
Accordance with the procedures outlined in ASTM E-84-24a.

SIGNED





AMERICAN FLAMECOAT INC.

520 Eagleton Downs Drive - D
Pineville, NC 28134
O: 704.405.2550
F: 704.543.9772
www.americanflamecoat.com

Client: ELITIS INC.
21-07 41st AVENUE
LON ISLAND CITY, NY 11101

INTRODUCTION:

This report presents test results of Flame Spread and Smoke Developed Value per ASTM E-84-24a. The report also includes Material Identification, Method of Preparation, Mounting and Conditioning of the specimens.

The tests were performed in accordance with the specifications set forth in ASTM E-84-24a, Standard Test Method for Surface Burning Characteristics of Building Materials, both as to equipment and test procedures. This test procedure is similar to UL-723, ANSI NO. 2.5, NFPA No. 255 and UBC 42-1.

The test results cover two parameters: Flame Spread and Smoke Developed Values during the 10-minute fire exposure. Inorganic cement board and red oak flooring are used as comparative standards, and their responses are assigned arbitrary values of 0 and 100 respectively.

PREPARATION AND CONDITIONING:

The test sample identified as ELITIS INC. - ESSENCE DE BOIS_DRYADES – RM 428 - (ADHERED) was prepared by adhering the material to 5/8" Type X gypsum board, glued using Roman – PRO-774 Clay Strippable Wallcovering Adhesive. This method of sample preparation is described in ASTM E2404-17, standard practice.

TEST PROCEDURE: Adhered

The tunnel was thoroughly pre-heated by burning natural gas. When the brick temperature, sensed by a floor thermocouple, had reached the prescribed 105 Fahrenheit +/- 5 Fahrenheit level, the sample was inserted in the tunnel and a test conducted in accordance with the standard ASTM E-84-24a procedures.

The operation of the tunnel was checked by performing a 10-minute test with inorganic board of the day of the test.

This test sample ***meets** the A.S.T.M. E-84 Standard

This test sample ***meets** the N.F.P.A. LIFE SAFETY CODE 101.



AMERICAN FLAMECOAT INC.

520 Eagleton Downs Drive - D
Pineville, NC 28134
O: 704.405.2550
F: 704.543.9772
www.americanflamecoat.com

Client: ELITIS INC.
21-07 41st AVENUE
LON ISLAND CITY, NY 11101

TEST RESULTS:

The test results calculated in accordance with ASTM E-84-24a for Flame Spread and Smoke Developed Values are as follows:

Test Specimen: ELITIS INC. – ESSENCE DE BOIS_DRYADES – RM 428
(ADHERED)

Flame Index = 15
Smoke Developed Value = 30

Observation: Tested Fabric Meets the Requirements for ASTM E-84-24


Rating: Class A

The National Fire Protection Association Life Safety Code 101, Section 6-5.3, “Interior Wall and Ceiling Finish Classification”, has a means of classifying materials with respect to Flame Spread and Smoke Developed when tested in accordance with NFPA 255, “Method of Test of Surface Burning Characteristics of Building Materials”, (ASTM E-84-24a)


The classifications are as follows:

Class A Interior Wall & Ceiling Finish:	Flame Spread-	0-25
	Smoke Developed-	0-450
Class B Interior Wall & Ceiling Finish:	Flame Spread-	26-75
	Smoke Developed-	0-450

Client: ELITIS INC.
Report#: 116730
Sample: ESSENCE DE BOIS_DRYADES_RM 428 - (ADHERED)



Client: ELITIS INC.
Report#: 116730
Sample: ESSENCE DE BOIS_DRYADES_RM 428 - (ADHERED)



Client: ELITIS INC.
Report#: 116730
Sample: ESSENCE DE BOIS_DRYADES_RM 428 - (ADHERED)

